



PRODUCT DESCRIPTION

Si gloss gold is a high quality oil paint with golden metallic effect, made of the best quality alkyds.

PRODUCT CHARACTERISTICS

- Golden metallic consistent glitter.
- Good gloss.
- Excellent coverage.

(Complies with the Egyptian Standard Specification No. 8563)

RECOMMENDED USE

Suits indoor and outdoor applications.

TYPE OF SURFACE

Wooden, Furniture, Concrete, Cementitious and Metallic surfaces.

TECHNICAL SPECIFICATION

Final Appearance	→ Glossy Gold
Viscosity	→ 50 ± 5 Kreds (at 25°C temperature and 50% humidity) → for white color, according to (ASTM D562-10 (2018))
Density	→ 1.00 ± 0.05 gm/cm ³ (at 25°C temperature and 50% humidity) → for white color, according to (ASTM D1475-13 (2020))
% Solids by Volume	→ 22 ± 2
Flash Point	→ 36°C ± 2

METHOD OF APPLICATION

Diluent	→ Sipes Spirit
% Dilution (by volume)	→ as needed
Application Tools	→ Roller, Brush, Sprayer

INSTRUCTIONS FOR THE USE OF AIRLESS SPRAYER

Pressure at nozzle	→ 150 Kg/cm ² (2100 psi)
Nozzle head	→ 0.013 – 0.021
Spray angle	→ 65° - 80°
Filter	→ Should be clean

FILM THICKNESS AND SPREADING RATE

	Min. Thickness	Max. Thickness	Average
Dry Film Thickness in Micron	30	40	35
Wet Film Thickness in Micron	136.3	181.8	159
Theoretical Spreading Rate (m ² /liter)	5 - 7		6

DRYING TIME

Generally, drying time depends on air draft, temperature, film thickness, selected colors, and number of coats. Data in schedule is measured at 25°C temperature and 50% humidity:

Surface Drying	3 hours approximately
Re-coating	16 hours approximately



SI GLOSS GOLD

RECOMMENDED COATING SYSTEM

All surfaces (new and old) should be clean and free from dust, oil, fat, ..etc.

FOR NEW METALLIC SURFACES

- 1 Coat suitable anti-rust primer.
- 1 Coat Hi matt / Si matt.
- 2 Coats Si Gloss Gold.

FOR NEW WOODEN SURFACES:

- 1 Coat Hi matt / Si matt after proper surface preparation.
- 2 Coats Si Gloss Gold.

FOR OLD SURFACES

- Clean the surface with water and suitable detergent. Make sure that the surface is fully dry, then follow the same application steps above.

CONDITIONS OF APPLICATION

Temperature of surface to be painted should not be lower than 10°C and 3°C above dew point. Appropriate air temperature and humidity should be observed.

GENERAL NOTES

1. Actual spreading rate depends on many factors like surface condition, effectiveness of application tool, film thickness, surface porosity, surface defects, temperature, quantity lost during application .. etc.
2. Maximum spreading rate for one coat may be realized by minimizing the dry film thickness, and vice versa.
3. Paint should be mixed before use if it is made of different batches.

STORAGE

Two years from production date, provided that proper storage conditions are observed. The product should be stored in compliance with storage instructions. The product should be stored in a cool well-ventilated environment, away from direct sun and heat. The container should be sealed tightly after use.

HEALTH AND SAFETY

Please read the protection instructions indicated on the container. Use in well-ventilated environment. Do not breathe or inhale mist. Avoid skin contact. Spillage on skin should be removed immediately with suitable cleanser and water. In case of contact with eyes, flush eye properly with abundant water and seek medical attention immediately. Keep away from the reach of children.

CLARIFICATION

The information in this Technical Specification is given to the best of our knowledge. It is based on laboratory tests and practical experience. Sipes takes no responsibility for consequences of breaching the instructions. The Company reserves the right to change data herein without notice.

Version: June 2025, Sipes Co. This version supersedes prior versions.